

Product Technical Information

CORKLINE® L5, L8, P5, P8, PF5, PF8

- ⊗ BINDER: Synthetic Rubber
- ⊗ CORK GRANULE SIZE: 1/2 mm
- ⊗ COLOR: Natural

TEST METHOD	TESTED PROPERTY	Uom	TEST RESULT
ASTM F 1315	Density	(kg/m ³)	600-750
ASTM D 2240	Hardness	SHORE A	55-70
ASTM F 36	Compressibility at 400 psi	(%)	30-50
ASTM F 36	Recovery (min)	(%)	> 80
ASTM F 152	Tensile strength (min)	(MPa)	
	Transversal direction	(MPa)	0,70
	Longitudinal direction	(MPa)	1,17
ASTM F 147	Flexibility, original (F=5)		No cracks
	ASTM No.1 Oil, 70 h at 100°C (F16)		No cracks
	Oven aged, 70 h at 100°C		No cracks
ASTM F 146	Volume change after immersion		
	ASTM No.1 Oil, 70 h at 100°C	(%)	-5 to +10
	ASTM No.3 Oil, 70 h at 100°C	(%)	+15 to +50
	ASTM Fuel A, 22 h at 23°C	(%)	0 to +10

FOLLOW THE LINE